

Hybrid-Lithium silicate with basic stain protection

Description

OBTEGO® R-30 is a highly reactive hybrid-lithium silicate with a basic protection against stains.

Properties

OBTEGO® R-30 penetrates deep into the surface and reacts then with free lime to calcium silicate hydrate (CSH), which progressively hydrates to a glass-like crystalline structure. Improved abrasion resistance, dust-free, impermeable and more resistance on the surface you get after the treatment with OBTEGO® R-30.

The hybrid-silica also reduces the penetration of liquids and dirt. Surfaces are easier to clean and the gloss is also increasing.

Basically, the product causes no or only slight color enhancement. The water absorption is reduced, the surface diffusion remains open.

Application

OBTEGO® R-30 is applicable to all cementitious floor coverings, such as grinded/polished and trowelled concrete floors / screeds, terrazzo tiles / terrazzo, etc. Applications are e.g. industrial floors, market halls, logistic centers, supermarkets and in private homes, indoor and outdoor use. For high-quality stain protection, we recommend our special impregnator OBTEGO® R-400 as an additional application.

Note: The acid sensitivity of the surfaces still remains, but will be reduced a little bit.

Processing

The surface to be treated must be dry and free from impurities. To ascertain the consumption make a separate sample area of the same surface. Apply the product with a airless sprayer and a suitable nozzle (0,2-0,3 is recommended). Work hand in hand with a second person, which is using a short hair roller (synthetic hairs, e.g. Polyamide) to get a homogenous treatment (optional). In most cases the use on a microfiber mop is also possible instead of the roller. Avoid puddles during application. Remove surplus material after approx. 20 minutes with auto scrubber machine or rub into the floor with a polishing pad. Drying time will be around 1-2 hours. For very high absorbent floors a second treatment with OBTEGO® R-30 is recommended. The second treatment **must** be wet in wet, because the product develop very quickly it's water repelling effect.

Note: Adjacent surfaces must be protected against splashes. Remove surplus material film before drying up. Clean equipment with water.

Processing temperature

Avoid direct solar radiation during processing. The surface temperature should be between 5 ° C and 35 ° C (40 – 100 F). Floor heating maybe turn off. Avoid direct moisture until the treatment is totally dry.

Drying time

The drying time (walkable) is between 1-2 hours. According to ambient temperature and humidity, drying time can vary. If there is an additional treatment of OBTEGO® R-400, drying time of OBTEGO® R-30 must be overnight (min. 12 hours).

Productiveness

Depending on the absorption following values are to be assumed. A second application halved the coverage. Reference value:

grinded/polished surface: approx. 15 - 25 m² / liter
trowelled surfaces: approx. 10 - 20 m² / liter

Storage

Protect from frost. Shelf-life in cool, dry and closed container is about 12 months. Opened cans should be worked up as soon as possible.

Environmental Protection

Not emty into drains. WGK 1 (low water endangering). Waste codes/waste designations according to EWC/AVV. 06 02 05* wastes from MFSU of other coatings (including ceramic materials): other bases. *Evidence for disposal must be provided. Dispose of waste according to applicable legislation. Consult the appropriate local waste disposal expert about waste disposal. Completely emptied packages can be recycled.

Security

OBTEGO® R-30 is harmless to health after drying up. A good ventilation should be provided during and after the processing. Observance of special security measures if the product will be use in a spraying application. Safety data sheet available for professional user on request.

Ingredients: lithium hydroxide, potassium methylsilanetriolate

Labelling according to Regulation (EC) No. 1272/2008 [CLP]. Causes skin irritation. Causes serious eye damage. Do not breathe dust/fume/gas/mist/vapours/spray. Wear protective gloves/protective clothing/eye protection/face protection. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If skin irritation occurs: Get medical advice/attention.

Identification marking for transportation:

PU	PU-marking	Transport documents
a	n.a.	n.a.

Packaging Unit (PU)

- a) 20 liter PE canister
- b) 200 liter barrel
- c) 1.000 liter container (IBC)

This information should only be a non-binding advice. The use of the products is based on local circumstances and on the surface itself. If there is no experience, and in cases of doubt, we recommend to try the product on a inconspicuous spot.